

Product Information

Polymeric PVC (white gloss, 85 µ) with grey-coloured solvent based adhesive (permanent), laminated on a two-sided PE-coated silicone paper liner (150 g/m²).

The PVC offers excellent dimensional stability.

The grey-coloured solvent based adhesive ensures a very good opacity.

Designed to be highly resistant to solvent ink aggression during printing process and to guarantee very good printing performance on any solvent, eco-solvent, UV or latex based ink-jet printer.

Particularly suitable for application on flat, curved and slightly corrugated surfaces.

Shelf Life

1 year when stored in the original packaging between 20°C and 25°C at 50% relative humidity.

Recommendations for Laminating

Please ensure the print is perfectly dry before laminating. We suggest to let the material dry for at least 48 hours after printing.

Recommended Overlamine Film

NL 50 High Gloss Overlamine
NL 51 Matt Overlamine

Technical Data

Carrier:	polymeric PVC, highly stabilised, calendered
Thickness:	85 µ +/- 5%
Adhesive:	grey-coloured solvent, permanent
Adhesion:	4,7 N/cm +/- 5%
Liner:	two-sided PE-coated silicone paper (150 g/m ²)
Tensile strength md:	>8,8 kN/m
Tensile strength cd:	>5,0 Kn/m
Application temperature:	+10 - +40°C
Service temperature:	-25°C to 82°C
Outdoor durability:	5 years (unprinted film)

Standard Dimensions

1370mm X 45.7M