

## Product Information

Polymeric PVC (white gloss, 85 µ) with clear solvent based adhesive (permanent), laminated on a two-sided PE-coated silicone paper liner (150 g/m<sup>2</sup>).

The PVC offers excellent dimensional stability and a superb level of whiteness in face film.

Designed to be highly resistant to solvent ink aggression during printing process and to guarantee very good printing performance on any solvent, eco-solvent, UV or latex based ink-jet printer.

Particularly suitable for application on flat, curved and slightly corrugated surfaces.

## Shelf Life

1 year when stored in the original packaging between 20°C and 25°C at 50% relative humidity.

## Recommendations for Laminating

Please ensure the print is perfectly dry before laminating. We suggest to let the material dry for at least 48 hours after printing.

## Recommended Overlaminates Film

NL 50 Gloss Overlaminates  
NL 51 Matt Overlaminates

## Technical Data

Carrier:	polymeric PVC, highly stabilised, calendared
Thickness:	85 µ +/- 5%
Adhesive:	clear solvent, permanent
Adhesion:	4,7 N/cm +/- 5%
Liner:	two-sided PE-coated silicone paper (150 g/m <sup>2</sup> )
Tensile strength md:	> 8,8 kN/m
Tensile strength cd:	> 5,0 Kn/m
Application temperature:	+10 - +40°C
Service temperature:	-25°C to 82°C
Outdoor durability:	5 years (unprinted film)

## Standard Dimensions

1370mm X 45.7M